

Wieland-SC5

CuZn25Al5Ni4Fe3

Slide Bearings

Wieland

Wieland-SC5

Special high-strength brass (wrought alloy) optimally suited for use in aluminium pistons as well as for joint bearings subjected to high loads in construction machinery, etc.

Composition (nominal)

Cu	66 %
Al	5 %
Mn	5 %
Fe	3 %
Ni	2 %
Zn	balance

Material designation

Wieland SC5
(patented material)

Physical properties (nominal)

Density	[g/cm ³]	7.8
Coefficient of thermal expansion (20-300 °C)	[10 ⁻⁶ /K]	20.5
Thermal conductivity	[W/m·K]	25
Modulus of elasticity (20 °C)	[GPa]	110

Max. load

approx. 200 MPa in the engine

Types available

Machined bushings

Tube dimensions for machined bushings

OD up to 100 mm
above please enquire

Wall thickness as a function of the OD

Mechanical properties (standard values)

Temper	
Hardness	[HB/HRB] 200/96
Tensile Strength R _m	[MPa] 700
0,2 %-proof stress R _{p0,2}	[MPa] 500
Elongation A5	[%] 7

1 MPa = 1 N/mm²

Wieland

WIELAND-WERKE AG
www.wieland.de

Slide Bearing
Division

89079 Ulm, Graf-Arco-Str. 36, Germany, Phone: +49 (0)731 944-0, Fax: +49 (0)731 944-2871

This leaflet is for your general information only and is not subject to revision. No claims can be derived from it unless there is evidence of intent or gross negligence. The data given are no warranty that the product is of a specified quality and they cannot replace expert advice or the customer's own tests.

0102 Fd