

Material Designation	
EN	CuZn39Pb2
UNS*	C37700

* Unified Numbering System (USA)

Chemical Composition (Reference)	
Cu	59 %
Pb	1.8 %
Zn	balance

Typical Applications
• Precision mechanical components
• Watch and clock parts
• Milled parts

Physical Properties*		
Electrical Conductivity	MS/m %IACS	14 24
Thermal Conductivity	W/(m·K)	109
Coefficient of Electrical Resistance**	10 ⁻³ /K	1.6
Coefficient of Thermal Expansion**	10 ⁻⁶ /K	21.1
Density	g/cm ³	8.43
Modulus of Elasticity	GPa	102
Specific Heat	J/(g·K)	0.377
Poisson's Ratio		0.34

* Reference values at room temperature

** Between 0 and 300 °C

Fabrication Properties	
Capacity for Being Hot Worked	excellent
Machinability	excellent
Capacity for Being Electroplated	excellent
Capacity for Being Hot-Dip Tinned	excellent
Soft Soldering	excellent
Resistance Welding	fair
Gas Shielded Arc Welding	less suitable
Laser Welding	less suitable

Corrosion Resistance


Good resistance to: fresh water, neutral or alkaline saline solutions, organic compounds as well as land, sea, and industrial atmosphere.

Not resistant to: acids, hydrous sulphur compounds, hydrous ammonia (stress corrosion cracking) in the non-stress-relieved condition. It is, however, susceptible to dezincification due to the two-phase α/β -structure.

Mechanical Properties					
Temper		R360	R420	R490	R560
Tensile Strength R_m	MPa	360–440	420–500	490–570	≥ 560
Yield Strength $R_{p0.2}$	MPa	≤ 270	≥ 270	≥ 420	≥ 510
Elongation A_{50mm}	%	≥ 30	≥ 12	–	–

Temper		H090	H120	H150	H175
Hardness HV		90–120	120–150	150–180	≥ 175

Electrical Conductivity




Wieland-Z30

CuZn39Pb2

C37700

Resistance to Softening



Vickers hardness
after heat treatment
(typical values)

Fatigue Strength

The fatigue strength is defined as the maximum bending stress amplitude which a material withstands for 10^7 load cycles under symmetrical alternate load without breaking. It is dependent on the temper tested and is about $\frac{1}{3}$ of the tensile strength R_m .

Types and Formats Available

- Standard coils with outside diameters up to 1400 mm
- Contour-milled strip
- Sheet
- Strip and sheet with protective coating

Dimensions Available

- Strip thickness from 0.20 mm
- Strip width from 3 mm, however min. 10 x strip thickness

Wieland-Werke AG

www.wieland.com

Rolled Products Division

Graf-Arco-Str. 36, 89079 Ulm, Germany, Phone +49 (0)731 944-0, Fax +49 (0)731 944-2772, info@wieland.de
Ziegeleiweg 20, 42555 Velbert-Langenberg, Germany, Phone +49 (0)731 944-0, Fax +49 (0)731 944-9270, info@wieland.de
Lantwattenstr. 11, 78007 Villingen-Schwenningen, Germany, Phone +49 (0)731 944-0, Fax +49 (0)731 944-7108, info@wieland.de

This leaflet is for your general information only and is not subject to revision. No claims can be derived from it unless there is evidence of intent or gross negligence. The data given are no warranty that the product is of a specified quality and they cannot replace expert advice or the customer's own tests.